

DriFast[™] STAIN

Oil-Modified Quick Dry Stain

A premium quality quick drying stain, compatible with Bona waterborne and all other Bona finish systems.

- 2 hour dry time*
- No bleed back
- 800 - 1,000 sf/gal coverage



Base Colors



Nutmeg



Early American




Red Mahogany



Natural




Golden Oak



Special Walnut




Jacobean




Ebony




Rosewood



Provincial



Antique Brown



Medium Brown



Cherry



Puritan Pine

Samples are shown on Red Oak finished with Bona Traffic[®] Semi-Gloss. Jobsite results may vary slightly, according to wood type and sanding procedures. Printed colors may vary slightly from actual stain colors. Always prepare test samples on wood.

* Under normal humidity and temperature conditions of 40-60% relative humidity at 65-80°F. Humidity and temperatures outside this range may extend drying times.



White**

** Allow 6 hours minimum dry time for White

Blending Custom Colors

DriFast™ STAIN

Oil-Modified Quick Dry Stain

To achieve custom colors with DriFast™ Stain, blend colors rather than adding universal tints. Blending maintains the essential properties of the dry time and application characteristics. Tinting with universal colorants can lead to less vibrant colors and unpredictable application results, and adhesion of the finish is at risk.


Mixing ratios for these blends are examples of the unlimited possibilities of custom wood tone colors you can achieve with DriFast™ Stain.

Blends




Autumn Gold

1 part Rosewood
1 part Golden Oak




Light Ebony

3 parts Natural
1 part Ebony




Dark Walnut

3 parts Jacobean
1 part Provincial




Spice

4 parts Provincial
1 part Jacobean



Antique

1 part Provincial
1 part Jacobean



Midnight Mahogany

3 parts Red Mahogany
1 part Ebony

A premium quality, quick-drying stain,
compatible with all Bona® waterborne and
all other Bona® finish systems.



- 2 hour dry time*
- No bleed back
- 800 - 1,000 sf/gal

Distributed By: